

A.8. PU + TEFLON PLATES

PDF	WAGU designation	Type	Polymer	Shore hardness ° A	Colour	Abrasion mm³	Specific weight g/cm³	Breaking strength N/mm²	Elongation at tear %	Available thicknesses mm	Del. time
-----	------------------	------	---------	--------------------	--------	--------------	-----------------------	-------------------------	----------------------	--------------------------	-----------

A.8.1. FLUI - TEC Polyurethan

A.8.1.1	FLUI - TEC Red 65 with / without BL	Both sides smooth	PU	65	Red	70	1,22		450	4 - 20	A
		Both sides smooth + 1EP top cover / ply									
		Both sides smooth + expanded metal grid									
A.8.1.2	FLUI - TEC Red 75 with / without BL	Both sides smooth	PU	75	Red	55	1,22		450	4 - 20	A
		Both sides smooth + 1EP top cover / ply									
		Both sides smooth + expanded metal grid									
A.8.1.3	FLUI - TEC Red 90 with / without BL	Both sides smooth	PU	90	Red	80	1,22		450	4 - 20	A
		Both sides smooth + 1EP top cover / ply									
		Both sides smooth + expanded metal grid									

A.8.2. FLON - TEC Teflon

A.8.2.1	FLON - TEC White with / without BL	Both sides smooth	PTFE		White					3 - 5	A
---------	------------------------------------	-------------------	------	--	-------	--	--	--	--	-------	---

L = available ex stock

A = manufactured to order (8-10 weeks)

M = minimum order quantity